

TECHNICAL DATA SHEET

DESCRIPTION

Freedom Select 15 is a cross linking, styrene-acrylic copolymer solution that helps concrete to attain full mix design properties. **Freedom Select 15** forms a film which will assist the curing of freshly placed concrete.

USES

Freedom Select 15 is formulated as an economical low viscosity, low solids formula for easy sprayability that meets ASTM C309 A for curing concrete.

FEATURES

- Clear
- Satin Finish
- Film Forming
- Water Based
- Breathable
- Low VOC
- Sprayable
- Non-yellowing
- Curing Aid
- Chemical Resistant

SURFACE PREPARATION

Clean dirt, wax, grease, oil and other contaminants from the surface. Make sure the surface is clean, dry and sound. Clean oily concrete with a cleaner/degreaser. Use a bristle brush for heavily oiled spots. If surface is slick, etch with an etcher. Rinse well with a pressure washer. Allow 24 hours to dry. Apply only when surface and air temperatures are above 50° F and below 90° F. Do not apply to excessively hot surfaces as rapid drying may cause streaking to form.

TECHNICAL

Meets ASTM C309
Meets AASHTO M 148
Water retention <0.55 kg/m²
15% Solids

MIXING

Shake well before use.

PLACING

Apply at substrate temperatures above 50° F. Apply with sprayer and back roll. On exterior concrete surfaces, you may use a medium nap roller. On smooth concrete use a short nap roller and cross roll in both directions. Thoroughly saturate surface. Apply additional coats as needed. See below for application rates. Foot traffic should be avoided for 4 hours. Vehicle traffic should be avoided for 48 hours. Cooler temperatures or increased humidity will slow the dry.

COVERAGE

Smooth Troweled:	300 ft ² per gallon
Textured or Stamped:	200 ft ² per gallon
Broom Swept:	200 ft ² per gallon

CLEANUP

Clean tools with water.

MAINTENANCE


Clean sealed surface with water only.

STORAGE

Protect from freezing. Recommended shelf life is one year.

SLIP RESISTANCE

For additional slip resistance, apply one coat. Mix grip additive and apply with second coat.



Cincinnati, OH: 513-489-9111 Dayton, OH: 937-866-9111
Norwood, OH: 513-651-9111 Columbus, OH: 614-224-9111
Erlanger, KY: 859-341-9111 Lexington, KY: 859-254-9111

PHYSICAL PROPERTIES

Appearance	Milky White Liquid
pH	8.5-9.5
Specific Gravity	1.05 g/cc
Lbs/Gal	8.35
Min. Temp	50 degrees
Water Resistance	Good
Viscosity	N/A
VOC	<180 g/L
Flash Point	N/A
DOT	Non-Regulated Material

CURE TIME

Dry to Touch	2 hours
Recoat	2 hours
Foot Traffic	4 hours
Wheel Traffic	48 hours

CONTAINER SIZES

5 gallon	(18.93 Liters)
55 gallon	(208.2 Liters)

HMIS

Health	1	Flammability	0
Reactivity	0	Protection	B

LIMITATIONS

Always test a small area for compatibility before proceeding.

Not recommended for clay brick, interior applications, natural stone, travertine, painted surfaces, tile, epoxy set stone, vertical surfaces, areas prone to drainage issues, or any surface not specifically recommended.

WARRANTY

Since Manufacturer has no control over handling, use or storage; no guarantee expressed or implied, is offered. The suitability of the product for use shall be solely up to the user. Manufacturer retains the right to venue.

WARNINGS

May be harmful if swallowed.

Precaution: Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Avoid breathing mist/vapors/spray. Wear eye protection. Do not eat, drink, or smoke while using product. **KEEP OUT OF REACH OF CHILDREN.**


FIRST AID

IF SWALLOWED: Get medical advice if you feel unwell. **IF ON SKIN (or hair):** Rinse skin with water/shower. **IF INHALED:** Remove person to fresh air and keep at rest in a position comfortable for breathing. If experiencing respiratory symptoms: Get medical advice. **IF IN EYE:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Get medical advice/attention if you feel unwell.

MANUFACTURER/TECHNICAL SERVICE

Exclusively manufactured for Janell Inc. by **CLEMONS CONCRETE COATINGS**

Contact your Janell representative for the most current product information. Always read and follow the warnings and instructions on the most current technical data sheets.



Cincinnati, OH: 513-489-9111 Dayton, OH: 937-866-9111
Norwood, OH: 513-651-9111 Columbus, OH: 614-224-9111
Erlanger, KY: 859-341-9111 Lexington, KY: 859-254-9111