

DESCRIPTION

Flowtopper is a stainable, industrial overlay designed for resurfacing and leveling interior concrete. The new surface will accept foot traffic in 6 hours and light rubber wheel traffic in 24 hours. **Flowtopper** is a blend of portland cement, high performance polymers, selected aggregates and proprietary admixtures. **Flowtopper** can be applied from 1/4" to 1/2" in a single lift.

USES

Flowtopper is ideal for applying over the surface of existing interior concrete to produce a new wearing surface. Use to resurface and repair:

- Cracked or spalled concrete
- Rough or uneven surfaces that need leveling
- Warehouse or light industrial floors that are in need of renovation for a hard, level surface

BENEFITS

- Durable: Contains no gypsum
- Color: Excellent base color to receive stain
- Versatile: Rehabilitates, repairs, resurfaces
- Adhesion: Polymer modified for increased adhesion to concrete surfaces
- Consistent: Strict Quality Control testing and standards

SURFACE PREPARATION

All surfaces in contact with **Flowtopper** shall be free of dirt, oil, grease, laitance and other contaminants that may act as bondbreakers. All unsound concrete should be removed to ensure a good bond. Concrete must be a minimum of 28 days old prior to placing **Flowtopper**.

Mechanically prepare the surface by shotblasting or scarifying to match ICRI CSP#5 (1/8" depth). Acid etching or the use of solvents is not an acceptable means of cleaning the substrate. Concrete must be abraded in order to receive primer and underlayment. Take special care in preparing very smooth, highly power troweled concrete. These surfaces must be prepared properly or the underlayment may delaminate.

After cleaning and profiling, test for moisture vapor emission rate (MVER - Ref. ASTM F1869) and concrete substrate's relative humidity (RH - Ref. ASTM F2170). The requirements of the floor covering and floor adhesive manufacturers must be followed with respect to, but not limited to, levels of moisture. Low substrate temperatures and/or high ambient humidity will extend drying time.

Repair holes and nonmoving cracks prior to application. Tensile strengths of the substrate must be greater than 72 psi (.5 MPa) per ASTM C1583. Install a bondbreaker where vertical surfaces meet the newly placed **Flowtopper**, such as self-adhering thick foam tape or similar product. **Note:** It is the responsibility of the installer/applicator to ensure the suitability of the product for its intended use.

Prime the surface with **RWB Bonding Agent OTR** at a rate of 500–600 ft²/gal when diluted 2:1 with clean, potable water. Apply evenly with a soft push broom. Do not use paint rollers, mops or spray equipment. Coverage rate of **RWB Bonding**

SURFACE PREPARATION (continued)

Agent OTR will vary depending on the porosity of the surface. Extremely absorbent concrete may require two applications of **RWB Bonding Agent OTR** to avoid the formation of "pinholes" in the underlayment. For this type of concrete, apply a first coat of **RWB Bonding Agent OTR** diluted 3:1 with water. Subsequent applications of **RWB Bonding Agent OTR** should be at the standard 2:1 ratio. Allow to dry to the touch before proceeding (2 to 4 hours). Protect primed substrate from foot traffic prior to installation. If applying lifts, prep and prime each lift with **RWB Bonding Agent OTR**. **Flowtopper** can be used over engineer approved wood subfloors including plywood, parquet and tongue and groove wood flooring with addition of metal lathe. Wood floors must be stable in order to provide a non-flexible surface. Fill joints and cracks to prevent seepage into undesired areas. Always apply a test area.

APPLICATION THICKNESS

Featheredge - 1", Up to 2" Extended

YIELD

50 lbs (22.7 kg) will fill approximately 0.43 ft³ (0.012 m³) when 4.5 quarts mixing water is used.

COVERAGE

One 50 lb (22.7 kg) bag will cover approximately 25 ft² at 1/4" thickness. Coverage may vary depending on porosity of surface.

MIXING

For best results, use a mechanical mixer with rotating blades or use a heavy duty 1/2" (15 mm) (or larger) low-speed, corded drill and mixing paddle #6 per ICRI Technical Guideline 320.5. Pre-wet mixer and empty excess water. Place 4.5 quarts of cool, clean potable water per 50 lb (22.7 kg) bag in mixer, then add dry material. Mix on low RPM for a total of 3 to 5 minutes until a homogeneous mixture is achieved. Mix only enough material that can be placed within working time. For placements greater than 1/2", **Flowtopper** must be extended 30%, by weight of powder, with clean, washed and dried 3/8" (1 cm) pea gravel. Add the aggregate during the last minute of mixing. Do not blend excess water as this will cause bleeding and segregation. Do not use any other admixtures or additives.

PLACING

Before application, close all doors, windows and HVAC vents to minimize air flow in the application area. Protect areas from direct sunlight. Pour or pump **Flowtopper** onto the primed substrate. Work into position with a long handled spreader, gauge rake and/or spiked roller. Immediately smooth the material with a "smoother". Wear spiked shoes to avoid leaving marks in the **Flowtopper**. The addition of aggregate will reduce the workability of the product and may make it necessary to install a neat coat to obtain a smooth surface. A second lift of non-extended material may be applied as soon as foot traffic can be supported. Profile or roughen subsequent lifts and re-prime with **RWB Bonding Agent OTR** to ensure a good bond.

Packaging: 50 lb (22.7 kg) bag, 63 bags per pallet



PHYSICAL PROPERTIES

All Physical Property testing performed in laboratory conditions of $73.5 \pm 3.5^{\circ}\text{F}$ ($23 \pm 2^{\circ}\text{C}$) and a relative humidity no less than 50% unless otherwise determined by the test method or specification. All results represent **Flowtopper** with 4.5 quarts water unless listed otherwise. Tests are conducted under standardized conditions for comparative purposes, and results may not be representative of performance under field conditions.

Property and Test Method		Results		
Compressive Strength		4 Hours	1 Day	7 Days
ASTM C109		2,000 psi (13.79 MPa)	2,800 psi (19.31 MPa)	3,200 psi (22.06 MPa)
Rate of Set	Self Leveling/ Healing Time	Working Time	Initial	Final
ASTM C1708	:15	:20	:30	1:30
Flexural Strength		7 Days	28 Days	
ASTM C348		1,100 psi (7.58 MPa)	1,300 psi (8.96 MPa)	

STORAGE

Normal cement storage and handling practices should be observed. Store material in an interior, cool, dry place. Shelf life is one year in original, unopened container.

LIMITATIONS

In addition to limitations already mentioned, please note the following. This product is for interior use only. Do not apply when the surface or ambient temperature is below 50°F (10°C) or expected to fall below 50°F (10°C) within 48 hours. Do not apply over surfaces that are frozen or contain frost. Do not apply over any active faults or cracks in the substrate without addressing any movement that may occur. Although crack repair is recommended prior to application, we cannot guarantee that cracks will not "telegraph" up through the overlayment. All moving joints, such as expansion joints, must be carried up through the new surface. Allow concrete to fully cure for 28 days before the use of this product. **Flowtopper** is not a resurfacing material for highways, streets, areas exposed to continuous traffic or industrial applications subject to hard or metal-wheeled traffic. Setting time will speed up in warm conditions and slow in cold conditions. **Flowtopper** makes an excellent base to receive concrete stains and sealers. As the performance of these systems varies greatly, it is essential that test areas be placed and evaluated to determine suitability prior to coating the entire area. In most cases, sealers can be applied 24 hours after the application of **Flowtopper**. **Note:** Most acid stains require 28 day curing time and slow in cold weather. For hot and cold weather applications, contact your Janell representative.

DANGER

This product contains Crystalline Silica (CAS# 14808-60-7) and Portland Cement (CAS# 65997-15-1). Harmful if swallowed. Causes skin irritation. Causes serious eye damage. May cause an allergic skin reaction. May cause cancer. May cause respiratory irritation. Causes damage to organs through prolonged or repeated exposure. Do not eat, drink or smoke when using this product. Wash hands thoroughly after handling. Contaminated work clothing must not be allowed out of the workplace. Do not handle until all safety precautions have been read and understood. Wear protective gloves/protective clothing/eye protection/face protection. Use only outdoors or in a well-ventilated area. Do not breathe dust. Keep away from children. Store locked up. Store in a well-ventilated place. Keep container tightly closed. Dispose of contents/container in accordance with local/regional/national/international regulations.

 **WARNING: Cancer and Reproductive Harm -**
www.P65Warnings.ca.gov

FIRST AID

If swallowed: Immediately call a poison center/doctor. Rinse mouth. If in eyes: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a poison center/doctor. If on skin: Wash with plenty of water. Take off contaminated clothing and wash it before reuse. If skin irritation or rash occurs: Get medical advice/attention. If inhaled: Remove person to fresh air and keep comfortable for breathing. Call a poison center/doctor if you feel unwell.

MANUFACTURER/TECHNICAL SERVICE

Exclusively manufactured for Janell Inc. by **US SPEC of Denver, CO**. Contact your Janell representative for the most current product information. Always read and follow the warnings and instructions on the most current technical data sheets.


JANELL

Cincinnati, OH: 513-489-9111

Norwood, OH: 513-651-9111

Erlanger, KY: 859-341-9111

Dayton, OH: 937-866-9111

Columbus, OH: 614-224-9111

Lexington, KY: 859-254-9111

LIMITED WARRANTY: The manufacturer warrants that this product is free from defects in material and workmanship, and will perform per the manufacturer product literature in effect at the time of purchase. This warranty is for one (1) year from the date of purchase. Any implied warranty of merchantability or fitness for a particular purpose is limited to the duration of this express warranty. This warranty applies only if the product is used, in strict accord with the manufacturer published instructions. The sole and exclusive remedy under this warranty is replacement of the defective product or refund of the purchase price, at the manufacturer's option. **CONSEQUENTIAL, SPECIAL, AND INCIDENTAL DAMAGES ARE NOT RECOVERABLE UNDER THIS WARRANTY.** All claims under this warranty must be submitted to the manufacturer by calling 303-778-7227. This warranty gives you specific legal rights, and you may also have other rights, which vary from state to state.